FIRESTOP CENTRE INNOVATIVE FIRESTOP SOLUTIONS

Authorised New Zealand Distributor Ph (09) 483 4000 www.firestopcentre.co.nz

Protecta EX Mortar Blank Seal in 100mm Concrete Floor

warringtonfire

FAS 210027 Page 38 AS1530.4-2014 AS4072.1-2005

Installation Instructions

- 1. Ensure the faces of the aperture opening are free of dust and any other contaminants. The faces may be moistened for better adhesion.
- 2. The seal can be positioned to either side of the construction or anywhere inbetween.
- 3. Install a stone wool shutter board to achieve the required thickness of mortar. Make sure that this achieves a very tight seal - any small openings should be sealed with Protecta® FR Acrylic
- 4. Pour clean water into a suitable mixing vessel and pour enough mortar to obtain the required consistency. Mix well to avoid lumps. Always add the mortar to the water, do not reverse this mixing process.
- 5. Once the desired consistency is achieved pour or trowel the mortar onto the shutter board making sure that it flows into all corners and around services. Apply a firm pressure to the mortar to eliminate any trapped air bubbles. Build up to the required depth.

co.nz		System/FPA Register ID# FC268	
		Products	Protecta EX Mortar Stone wool shutter
	Protecta EX Mortar Minimum seal depth 100mm Maximum aperture 1200x2400mm	Application	Fire stopping of blanks in rigid floors
		Construction	Minimum floor thickness of 100mm and comprise aerated concrete or concrete with a minimum density of 650kg/m ³ .
		Fire & Sound classification	
		Blank seal in standard 1200 x 2400mm aperture FRR -/240/240	
Permitted Aperture Sizes		Sound reductior	ı (seal only) STC 64
Where standard aperture sizes of 1200mm by 2400mm are stated, the following additional sizes are automatically permitted: 1100mm x 2900mm 1000mm x 4000mm 800mm x infinite length			$\langle \rangle$
Loadbearing Properties: <u>NOTE</u> following for Health and Safety requirements Soft body impact, serviceability 500Nm. Soft body impact, safety in use 700Nm. Hard body impact serviceability 6Nm. Hard body impact, safety in use 10Nm. Concentrated load to 15kN on size up to 1500mm x1000mm (no failure), 4.85kN on sizes up to 1200mm x 2400mm.			, 15 St Andrews Road,
, we reserve the right to modify, alter or change	For all technical details on the products specified please refer to the technical data sheets that can	Huddersfield, West Yorkshire, HD1 6SB Email: post.uk@polyseam.com	
ed in this document is given in good faith and is purposes only. As Polyseam has no control over nditions, no warranties, expressed or implied, is	be found on www.firestopcentre.co.nz Signed and approved:	Sheet size: A4	Drawn date & no: 23/5/21
nentioned or referred to herein and no liability n the use of the information given.		Scale:	Drawn by:
		NTS	K.B

warringtonfire **E TA**

ETA 21/0071 FAS 210027 AS1530.4-2014 AS4072.1-2005

As a part of our policy of on-going product development and testing, we reproduct specifications without giving notice. All information contained in th provided for guidance only. Any drawings provided are for illustrative purpos the methods or competence of installation and of prevailing site conditions intended to be given as to the actual performance of the product mentior whatsoever will be accepted for any loss, damage or injury arising from the u